



Standard Specification for Exterior Solar Radiation Control Coatings on Buildings¹

This standard is issued under the fixed designation C 1483; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 The purpose of this specification is to provide general requirements for products used to reduce thermal loads on buildings by reflecting solar radiation from roofs and walls. Radiation control coating (RCC) is a liquid applied coating having a solar reflectance of 0.8 and an ambient temperature infrared emittance of at least 0.8.

1.2 This specification covers the physical and mechanical properties of liquid-applied radiation control coatings (RCCs) designed for exterior application on buildings or other structures, where ambient air temperatures range from -34 to 54°C (-30 to 130°F). The specification also includes the testing procedures by which the acceptability of the material may be determined.

1.3 The products that comply with this specification may be used for other applications and have other properties not covered by this specification. In such cases, it is advisable to check other specifications that address the applications of interest.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:²

- C 168 Terminology Relating to Thermal Insulation Materials
- C 419 Practice for Making and Curing Test Specimens of Mastic Thermal Insulation Coatings
- C 461 Test Methods for Mastics and Coatings Used With Thermal Insulation
- C 1371 Test Method for Determination of Emittance of

- Materials Near Room Temperatures Using Portable Emitters
- D 471 Test Method for Rubber Property—Effect of Liquids
- D 903 Test Method for Peel or Stripping Strength of Adhesive Bonds
- D 2370 Test Method for Tensile Properties of Organic Coatings
- D 2697 Test Method for Volume of Nonvolatile Matter in Clear or Pigmented Coatings
- D 3274 Method for Evaluating Degree of Surface Disfigurement of Paint Films by Microbial (Fungal or Algal) Growth or Soil and Dirt Accumulation
- E 84 Test Method for Surface Burning Characteristics of Building Materials
- E 96 Test Methods for Water Vapor Transmission of Materials
- E 349 Terminology Relating to Space Simulation
- E 903 Test Method for Solar Absorptance, Reflectance and Transmission of Materials Using Integrating Spheres
- E 1175 Test Method for Determining Solar and Photopic Reflectance, Transmittance and Absorptance of Materials Using Large Diameter Integrating Spheres
- G 155 Practice for Operating Xenon-Arc light Apparatus for Exposure of Nonmetallic Materials

3. Terminology

3.1 *Definitions*—Terminology C 168 and E 349 shall apply to this specification.

3.2 *Definitions of Terms Specific to This Standard:*

3.2.1 *radiation control coating (RCC), n*—a radiation control coating is a material that is designed to have a high solar reflectance (above 0.8) and a high infrared emittance (above 0.8) for long wavelength radiation.

3.2.2 *solar reflectance, n*—solar reflectance is the fraction of incident solar radiation that is reflected.

4. Significance and Use

4.1 It is recognized that the solar reflectance of RCCs will be reduced by soiling, which is caused by the accumulation of dirt, dust and other contaminants on the surface. The soiling, on the roof, will differ from location to location and from environment to environment. It is possible that soiling rates are affected by the slope of the surface, the roughness of the surface, the characteristics of the dust in the air, the dust

¹ This specification is under the jurisdiction of ASTM Committee C16 on Thermal Insulation and is the direct responsibility of Subcommittee C16.21 on Reflective Insulation.

Current edition approved Feb. 1, 2004. Published March 2004. Originally approved in 2000 as C 1483–00.

² For referenced ASTM standards, visit the ASTM website, www.astm.org, or contact ASTM Customer Service at service@astm.org. For *Annual Book of ASTM Standards* volume information, refer to the standard's Document Summary page on the ASTM website.

content of the air and the degree of growth of mildew and other organisms on the surface. Low slopes, rough surfaces, dusty air and persistent moisture and conditions of high humidity are all conducive to soiling. At this time there are insufficient observations available to predict the amount of soiling for a given locale or the effect of the soiling on solar reflectance. Nor have any test procedures been developed to determine the ease with which the RCCs can be cleaned and the degree to which the solar reflectance can be restored. It is suggested that users examine the potential for soiling at the application site and determine if the cleaning methods suggested by the manufacturer are likely to be adequate to maintain solar reflectance at an acceptable level, for the type of soiling expected

5. Materials and Manufacture

5.1 *Composition*—The manufactured product shall be in liquid form, suitable for application to exterior surfaces by brushing, rolling, or spraying. The product shall be a elastomeric or resinous material, to which various pigments, diluents, and other additives have been added to give the desired properties.

6. Physical and Mechanical Properties

6.1 *Total Solids*—The total solids of the liquid product shall not be less than 25 %, by weight, and shall be determined in accordance with 8.1.

6.2 *Solids Volume*—The total solids in the liquid product shall not be less than 25 %, by volume, as determined in accordance with 8.2.

6.3 *Solar Reflectance*—The solar reflectance of the cured coating shall be determined in accordance with 8.3. The solar reflectance of the cured coating shall be no less than 0.8.

6.4 *Infrared Emittance*—Infrared emittance, at ambient temperature, shall be determined in accordance with 8.4. The ambient temperature infrared emittance of the cured coating shall be no less than 0.8.

6.5 *Elongation*—The elongation of the cured coating shall be determined in accordance with 8.5.

6.5.1 The elongation of the cured coating shall be greater than 200 % and 100 % at testing temperatures of 25 and -18°C (77 and 0°F) respectively.

6.5.2 The elongation of the coating after UV exposure shall not be less than 80 % of the values obtained at 25 and -18°C (77 and 0°F) on the cured coating.

6.6 *Adhesion*—The adhesion of the coating shall be determined in accordance with 8.6. The adhesion of the cured coating shall be reported for each of the substrates tested.

6.7 *Water Vapor Permeance*—The water vapor permeance of the cured coating shall be determined in accordance with 8.7. The water vapor permeance values shall be reported for the thickness tested but in no case shall be greater than 20 perms.

6.8 *Flame Retardancy*—The flame retardancy of the cured coating shall be determined in accordance with 8.8 and shall be tested on a substrate typical of final installation. Flame spread and smoke development shall be no greater than that required by local code requirement.

6.9 *Fungi Resistance*—The fungi resistance of the cured coating shall be determined and found acceptable in accordance with 8.9.

6.10 *Water Absorption*—Water absorption of the cured coating shall be determined in accordance with 8.10.

6.11 *Cured Sample Thickness*—The cured sample thickness shall be determined in accordance with 8.11.

6.12 *Outdoor Durability*—The outdoor durability shall be determined in accordance with 8.12.

7. Sample Preparation

7.1 *Sampling*—Samples for testing shall be taken from the original containers immediately after stirring the material to a uniform condition.

7.2 *Cured Sample Preparation*—For tests to be performed on specimen of cured (dry) product, the thickness of the specimen will be no less than the manufacturer's recommended cured coating thickness. The cured coating specimen shall be prepared on a substrate suitable for the intended test. Example of these substrates are metal, stucco or black asphalt.

7.3 Cured values shall be determined in accordance with 8.11.

8. Test Methods

8.1 *Total Solids (by Weight)*—Determine the total solids of the wet product in accordance with Test Methods C 461, Section 8.

8.2 *Solids Volume*—Determine the solids volume of the wet product in accordance with Test Method D 2697.

8.3 *Solar Reflectance*—The solar reflectance shall be determined on samples in the cured condition placed on low solar reflectance substrates in accordance with either Test Method E 903 or E 1175. This may be done with a solar reflectometer.

8.4 *Total Hemispherical Emittance*—Total hemispherical emittance, at ambient temperature, shall be determined on cured samples placed on low emittance substrates in accordance with Test Method C 1371.

8.5 *Elongation*—Elongation tests shall be performed on cured samples before and after 3000-h exposure to ultraviolet (UV) radiation in accordance with Test Method D 2370 and Practice G 155 (without water).

8.6 *Adhesion*—Adhesion tests shall be performed on cured samples in accordance with Test Method D 903.

8.7 *Water Vapor Permeance*—Determine the water vapor permeance on cured samples in accordance with Test Methods E 96, desiccant method.

8.8 *Flammability*—Determine the flammability of cured samples in accordance with Test Method E 84.

8.9 *Fungi Resistance*—Determine the fungi resistance of the cured material in accordance with Test Method D 3274.

8.10 *Water Absorption*—Determine the water absorption of the cured product in accordance with Test Method D 471.

8.11 *Cured Samples Thickness*—Determine cured sample thickness in accordance with Practice C 419.

8.12 *Outdoor Durability*—Determine the outdoor durability in accordance with Practice G 26.

9. Inspection and Rejection

9.1 Inspection and rejection of material shall be agreed upon between the purchaser and the seller as part of the purchase contract.

10. Packaging and Package Marking

10.1 *Packaging*—Unless otherwise agreed or specified, materials shall be packaged in the manufacturers standard commercial containers.

10.2 *Marking*—The marking shall be clear and legible. Unless otherwise specified, each container shall be marked with the date of manufacture, material name, ASTM designation, manufacturer's name or trademark, and coverage of material in container.

11. Keywords

11.1 emittance; radiation control coating; solar reflectance; solids volume; total solids

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).