



Standard Guide to Evaluation of Optical Properties of Powder Coatings¹

This standard is issued under the fixed designation D 5382; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

The term optical properties of powder coatings refers to those properties associated with the interaction of visible light with the coatings. These properties include, but are not limited to, color, color difference, gloss, and metamerism. Coating powder users and producers may sometimes be overwhelmed by the sheer number of standard practices and standard test methods available for the evaluation of the optical properties of the finished coatings.

This guide is intended to lead the user to each of the practices and test methods needed, once the user decides whether the evaluation is to be by visible means or by instrumental means. Further, the user must decide which of the several optical properties mentioned above are to be evaluated. This guide will lead the user to the applicable practices and test methods for the properties chosen by the means selected.

1. Scope *

1.1 This standard provides the user with a guide to the various available practices and test methods for the evaluation of color, color difference, gloss, and metamerism by both visual and by instrumental means.

1.2 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- D 523 Test Method for Specular Gloss²
- D 1535 Practice for Specifying Color by the Munsell System²
- D 1729 Practice for Visual Appraisal of Colors and Color Differences of Diffusely-Illuminated Opaque Materials²
- D 2244 Test Method for Calculation of Color Differences from Instrumentally Measured Color Coordinates²
- D 2616 Test Method for Evaluation of Visual Color Difference With a Gray Scale²
- D 3134 Practice for Establishing Color and Gloss Tolerances²

D 4039 Test Method for Reflection Haze of High-Gloss Surfaces²

D 4086 Practice for Visual Evaluation of Metamerism²

D 4449 Test Method for Visual Evaluation of Gloss Differences Between Surfaces of Similar Appearance²

D 5767 Test Methods for Instrumental Measurement of Distinctness-of-Image Gloss of Coating Surfaces²

E 284 Terminology of Appearance²

E 308 Practice for Computing the Colors of Objects by Using the CIE System²

E 430 Test Methods for Measurement of Gloss of High-Gloss Surfaces by Goniophotometry²

E 1247 Test Method for Identifying Fluorescence in Object-Color Specimens by Spectrophotometry²

E 1331 Test Method for Reflectance Factor and Color by Spectrophotometry Using Hemispherical Geometry²

E 1345 Practice for Reducing the Effect of Variability of Color Measurement by Use of Multiple Measurements²

E 1347 Test Method for Color and Color-Difference Measurement by Tristimulus (Filter) Colorimetry²

E 1349 Test Method for Reflectance Factor and Color by Spectrophotometry Using Bidirectional Geometry²

E 1360 Practice for Specifying Color by Using the Optical Society of America Uniform Color Scales System²

E 1541 Practice for Specifying and Matching Color by Using the Colorcurve System²

3. Terminology

3.1 The definitions in Terminology E 284 are applicable to the appearance terms used in this standard. The following

¹ This guide is under the jurisdiction of ASTM Committee D01 on Paint and Related Coatings, Materials, and Applications and is the direct responsibility of Subcommittee D01.51 on Powder Coatings.

Current edition approved Jan. 10, 2002. Published March 2002. Originally published as D 5382 – 93. Last previous edition D 5382 – 95.

² *Annual Book of ASTM Standards*, Vol 06.01.

*A Summary of Changes section appears at the end of this standard.

terms from Terminology E 284 are specific to this standard.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *coating powder(s), n*—finely divided particles of resin, either thermoplastic or thermosetting, generally incorporating pigments, fillers, and additives and remaining finely divided during storage under suitable conditions, which, after fusing and possibly curing, give a continuous film.

3.2.2 *color, n*—(2) *perceived*, attribute of visual perception that can be described by color names such as white, gray, black, yellow, brown, vivid red, deep reddish purple, or by combinations of such names.

(3) *psychophysical*, characteristics of a color stimulus (that is, light producing a sensation of color) denoted by a colorimetric specification with three values, such as tristimulus values.

3.2.3 *color difference, n*—(1) *perceived*, the magnitude and character of the difference between two colors described by such terms as redder, bluer, lighter, darker, grayer, or cleaner.

(2) *computed*, the magnitude and direction of the difference between two psychophysical color stimuli and their components computed from tristimulus values, or chromaticity coordinates and luminance factor, by means of a specified set of color-difference equations.

3.2.4 *gloss, n*—angular selectivity of reflectance, involving surface reflected light, responsible for the degree to which reflected highlights or images of objects may be seen as superimposed on a surface.

3.2.5 *metamerism, n*—property of two specimens that match under a specified illuminator and to a specified observer and whose spectral reflectances or transmittances differ in the visible wavelengths.

3.2.6 *powder coatings, n*—coatings which are protective or decorative, or both, formed by the application of a coating powder to a substrate and fused in a continuous film by the application of heat or radiant energy.

4. Visual Evaluation of Optical Properties

4.1 *Visual Gloss*: To assess the visual gloss difference between two powder coated surfaces of similar appearance use Test Method D 4449.

4.2 *Color*: To obtain the color notation of a specimen in the Munsell Color Order System use Practice D 1535. To obtain the color notation of a specimen in the Optical Society of America Uniform Color System use Practice E 1360. To obtain the color notation of a specimen in the Colorcurve System use Practice E 1541.

4.3 *Color Difference*: Practice D 1729 will provide visual color difference in descriptive terms. If it is desirable to quantify the color difference visually, use Test Method D 2616.

4.4 *Metamerism*: Carry out visual evaluation of a metameric pair of specimens by Practice D 4086.

4.5 *Miscellaneous Optical Properties*: Evaluate visually reflection haze of high gloss surfaces, as well as distinctness-of-image gloss, by Test Method D 4449.

5. Instrumental Evaluation of Optical Properties

5.1 *Specular Gloss*: Measure the specular gloss of a powder coating by Test Method D 523.

5.2 *Color*: If filter photometry is to be employed, use Test Method E 1347. If spectrophotometric means are to be employed, acquire spectral data on instruments having 45° illumination and normal viewing by Test Method E 1349, and on instruments having an integrating sphere by Test Method E 1331. The spectrophotometric data are then integrated to tristimulus values by Practice E 308.

5.3 *Color Difference*: Evaluate the color difference between two powder-coating specimens by Test Method D 2244 using the tristimulus values acquired in 5.2.

5.4 *Metamerism*: Although Practice D 4086 is a visual method, Note 1 to Section 7 in that practice describes a method for comparison of spectral curves of two specimens to detect the presence of metamerism.

5.5 *Miscellaneous Optical Properties and Methods*: Evaluate reflection haze of high gloss surfaces instrumentally by Test Method D 4039. Evaluate distinctness-of-image gloss of high gloss surfaces by Test Methods E 430 or by Test Methods D 5767. Fluorescence in a powder coating may be identified by Test Method E 1247. Establish color and gloss tolerances by Practice D 3134. Practice E 1345 gives methods of reducing the variability of color measurements by making multiple measurements.

6. Report

6.1 Reports that may be required are contained in each of several referenced standards that may be utilized as a result of following this guide.

7. Keywords

7.1 appearance; coating powders; color; color difference; gloss; metamerism; powder coatings



D 5382

SUMMARY OF CHANGES

Committee D01 has identified the location of selected changes to this standard since the last issue (D 5382 - 95) that may impact the use of this standard.

Minor changes to:

(1) Introduction.

(2) D 5767 added to Section 2.

(3) Added coating powder(s) and powder coatings to Section 3.

(4) Appearance and coating powders added to Section 7.

ASTM International takes no position respecting the validity of any patent rights asserted in connection with any item mentioned in this standard. Users of this standard are expressly advised that determination of the validity of any such patent rights, and the risk of infringement of such rights, are entirely their own responsibility.

This standard is subject to revision at any time by the responsible technical committee and must be reviewed every five years and if not revised, either reapproved or withdrawn. Your comments are invited either for revision of this standard or for additional standards and should be addressed to ASTM International Headquarters. Your comments will receive careful consideration at a meeting of the responsible technical committee, which you may attend. If you feel that your comments have not received a fair hearing you should make your views known to the ASTM Committee on Standards, at the address shown below.

This standard is copyrighted by ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States. Individual reprints (single or multiple copies) of this standard may be obtained by contacting ASTM at the above address or at 610-832-9585 (phone), 610-832-9555 (fax), or service@astm.org (e-mail); or through the ASTM website (www.astm.org).